

Reflectix® Insulation

Technical Information DBWEF48100 / DBWEF48050

Concrete Slab Insulation

Reflectix® Concrete Pad consist of seven layers. The first layer of white poly is bonded to foil to protect from lime in curing concrete. Followed by layers of clear poly and bubbles.

Technical Data:

Temperature Range:	-30 degrees to + 180 degrees F
Nominal Thickness:	5/16 inch (.312)
Weight:	1.25 oz./sq. ft.
Linear Shrinkage:	None
Water Vapor Transmission (ASTM E 96):	0.02 Perms
Puncture Resistance:	60 lb./in.
Mold and Mildew:	No Growth
Tensile Strength:	3.7 N/mm
Pliability:	No Cracking
Physical Properties - Compression	6%

Reflectix, Inc.

A Division of Balcan Innovations Inc.

#1 School Street (P.O. Box 108) Markleville, IN 46056 • Ph: (800) 879-3645 (US/Can) or (765) 533-4332 • Fax: (765) 533-2327

www.reflectixinc.com • Email: customerservice@reflectixinc.com

T60 Revised 0922