

Reflectix® Insulation

Technical Information RB4812550

Radiant Barrier with Woven Polyethylene Fabric, Perforated

Reflectix® Radiant Barrier consists of two outer layers of 96% reflective metalized film bonded together enclosing a woven polyethylene fabric, perforated.

Technical Data:

Weight:	15.0 lbs per 500 sq. ft.
Flame Spread Index (ASTM E 84):	Less than 25
Smoke Developed Index (ASTM E 84):	Less than 50
Fire Rating:	Class A/Class 1
Reflectance (IR):	96%
Fungi Resistance:	No Growth
Emittance:	0.04
Pliability:	No Cracking or Delamination
Bleeding and Delamination:	Passed
Adhesive Performance:	No Bleeding or Delamination
Corrosivity:	Pass
Product Thickness:	0.006
Permeance:	6.3 Perms
Tensile/Tear Strength:	
Length:	13.23 Pounds Force
Width:	13.98 Pounds Force

Reflectix, Inc.

A Division of Balcan Innovations Inc.

#1 School Street (P.O. Box 108) Markleville, IN 46056 • Ph: (800) 879-3645 (US/Can) or (765) 533-4332 • Fax: (765) 533-2327

www.reflectixinc.com • Email: customerservice@reflectixinc.com

T92 Revised 102022