

# Reflectix® Insulation

## Technical Information RB4812550

### Radiant Barrier with Woven Polyethylene Fabric, Perforated

Reflectix® Radiant Barrier consists of two outer layers of 94% + reflective metalized film bonded together enclosing a woven polyethylene fabric, perforated.

#### Technical Data:

Weight:	15.0 lbs per 500 sq. ft.
Flame Spread Index (ASTM E 84):	Less than 25
Smoke Developed Index (ASTM E 84):	Less than 50
Fire Rating:	Class A/Class 1
Reflectance (IR):	94% +
Fungi Resistance:	No Growth
Emittance:	Less than 0.06
Pliability:	No Cracking or Delamination
Bleeding and Delamination:	Passed
Adhesive Performance:	No Bleeding or Delamination
Corrosivity:	Pass
Product Thickness:	0.006
Permeance:	6.3 Perms
Tensile/Tear Strength:	
Length:	13.23 Pounds Force
Width:	13.98 Pounds Force

Reflectix, Inc. #1 School Street (P.O. Box 108) Markleville, IN 46056  
Ph: (800) 879-3645 (US/Can) or (765) 533-4332 • Fax: (765) 533-2327  
[www.reflectixinc.com](http://www.reflectixinc.com) • Email: [customerservice@reflectixinc.com](mailto:customerservice@reflectixinc.com)

"Like Us" at [www.facebook.com/ReflectixInsulation](https://www.facebook.com/ReflectixInsulation) • [www.youtube.com/ReflectixInsulation](https://www.youtube.com/ReflectixInsulation) • [www.pinterest.com/reflectixinc](https://www.pinterest.com/reflectixinc)