

Reflectix® Insulation

Technical Information RB4812550

Radiant Barrier with Woven Polyethylene Fabric, Perforated

Reflectix® Radiant Barrier consists of two outer layers of 96% reflective metalized film bonded together enclosing a woven polyethylene fabric, perforated.

Technical Data:

| | |
|---|------------------------------------|
| Weight: | 15.0 lbs per 500 sq. ft. |
| Flame Spread Index (ASTM E 84): | Less than 25 |
| Smoke Developed Index (ASTM E 84): | Less than 50 |
| Fire Rating: | Class A/Class 1 |
| Reflectance (IR): | 96% |
| Fungi Resistance: | No Growth |
| Emittance: | 0.04 |
| Pliability: | No Cracking or Delamination |
| Bleeding and Delamination: | Passed |
| Adhesive Performance: | No Bleeding or Delamination |
| Corrosivity: | Pass |
| Product Thickness: | 0.006 |
| Permeance: | 6.3 Perms |
| Tensile/Tear Strength: | |
| Length: | 13.23 Pounds Force |
| Width: | 13.98 Pounds Force |

Reflectix, Inc. #1 School Street (P.O. Box 108) Markleville, IN 46056
Ph: (800) 879-3645 (US/Can) or (765) 533-4332 • Fax: (765) 533-2327
www.reflectixinc.com • Email: customerservice@reflectixinc.com

www.youtube.com/ReflectixInsulation • "Like Us" at www.facebook.com/ReflectixInsulation • www.pinterest.com/reflectixinc